

Siliguard Coat

Electrically conductive coating for impressed current cathodic protection of steel in concrete

Technical Data Sheet

Product application

Siliguard Coat is an electrically conductive coating specifically designed for giving electro-chemical protection, known as impressed current cathodic protection (ICCP), for the prevention of corrosion of the concrete steel reinforcement according to the international standard ISO/EN 12696. The current required for cathodic protection is provided by a DC power source supplied through an anode feeder cable.

Product description

Siliguard Coat is a one component inorganic low alkaline aqueous composite paint for active corrosion control of steel in concrete. Once applied the paint -consisting of concrete's own ingredients with an open porous structure- guarantees excellent adhesion and acid proof properties.

Siliguard coat can be applied either by brushing, rolling or spraying.

Primary anodes like Cu/Nb- or Ti-wire/stripp need to be embedded into the paint for a uniform current distribution.

Protection of the steel in concrete is achieved by applying a voltage in the range of 2 - 5 Volts between the paint and the steel in concrete.

The anodic electrochemical reactions taking place on the electrode material produce hydrogen-ions (H^+) and oxygen gas (O_2). The acidification by the anode reaction will not harm the paint and the oxygen gas will be easily dissipated by the natural porosity of the paint.

Features

- 1K-Water based solution with low alkali content.
- Solvent free (no VOC)
- Non inflammable and incombustible.
- Long shelf life.
- Good penetration.
- Open porous structure.
- Sealing is based on formation of polysilicics and carbonates.
- Reaction products in the substrate are not water soluble.
- Reaction products are acid resistant.

Siliguard Coat

Technical Information

Siliguard Coat	Density	1,36 g/cm ³
Solids by volume		50%
Expected service life		minimum 20 years
pH		12.5
wet film thickness		600 um
dry film thickness		300 um
theoretical spreading rate		1,2 m ² /l
Adhesion strength (against concrete)		> 2 MPa
Water vapour diffusion : μ_{H_2O}		250
Water absorption rate		350gr/m ² /h ^{0.5}
Water vapour diffusion thickness : sd		0,025 (100 um)
Electric Resistivity		Appr. 1 Ohm.cm
Voltage drop in the coating		< 5% / meter (300 um)
Expected service life		> 20 years
Siliguard Primer	Density	1,10 g/cm ³
Solids by volume		13%
pH		11
wet film thickness		100 um
dry film thickness		10 um
theoretical spreading rate		5 m ² /l
Adhesion strength (against concrete)		> 2 MPa
Water vapour diffusion : μ_{H_2O}		100
Water absorption rate		500gr/m ² /h ^{0.5}
Water vapour diffusion thickness : sd		0,005 (50 um)

ICCP design

In line with other CP systems, a CP system based on Siliguard Coat should be designed by qualified and certified engineers and installed by qualified and experienced contractors. Please refer to the international standard EN/ISO 12696 "Cathodic protection of steel in concrete" and EN 15257 "Competence levels and certification of cathodic protection personnel".

For further recommendations refer to the General Description and Installation Guidelines.

CorrPRE Engineering BV, Zuidbaan 509, 2841MD, Moordrecht, Netherlands

Revision Nr.
03

Revision date
27th April 2017

Approved
R. Giorgini

All technical data stated in this Technical Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control. The information, and, in particular, the recommendations relating to the application and end-use of CorrPRE's products, are given in good faith based on CorrPRE's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with CorrPRE's recommendations.