

Technical Data Sheet

SiliGrout (ICCP)

Acid-resistant mineral-based ICCP grout.



Description

This 100% inorganic grout is acid-resistant and composed of mineral binders and silica fillers. The mortar hardens by internal chemical action, producing an insoluble silica gel. It is resistant to most acids and salts and completely inert to all organic solvents. Used for discrete anodes for impressed current cathodic protection of steel in concrete.

Features of application

- silicate technology
- environmentally friendly
- mineral based
- very low emission EC 1PLUS R
- fast curing and tension-relieved
- high flowability
- high abrasion resistance
- easy application
- processible by machine

*Reseal opened containers immediately and use within a very short time. The original packing is storable for 12 months in dry and controlled temperature areas (recommended 10 – 25 °C).

Applications

Prior to application, ensure that the surface is stable and has sufficient surface tensile strength. The surface should also be ready for coating, dry or matt damp, clean and free from all kinds of debris, grease and dust.

The adhesive strength of the substrate must be at least 1,5 N/mm². The application has to be protected from drying too quickly (due to drafts or intense heat from the sun) for at least 24 hours.

There is no mandatory hazard labeling for **SiliGrout**. Avoid inhaling dust when opening packaging. Protect skin and eyes during the mixing process.

CE 1410 EN	EN 13813 CT-C40-F10-A15
SELF-LEVELING MINERAL BASED MORTAR	
FIRE BEHAVIOR	A1
COMPRESSIVE STRENGTH	C40
FLEXURAL STRENGTH	F10
RELEASE OF CORROSIVE SUBSTANCES	CT

Technical Data Sheet

SILIGROUT

MIXING RATIO	4 - 4.5 LITRES OF WATER PER 25 KG OF POWDER
PROCESSING TIME AT 200 C	APPR. 40 MIN.
PROCESSING TEMPERATURE	+50 °C TO +350 °C
LOADABILITY	APPR. AFTER 4 HRS
COMPRESSIVE STRENGTH	40 N/MM ² (> 28 DAYS)
FLEXURAL TENSILE STRENGTH	12 N/MM ² (> 28 DAYS)
SPECIFIC GRAVITY	FRESH MORTAR 2,0 G/CM ³
CONSUMPTION	APPR. 1.8 KG/M ² PER 1MM THICKNESS
LONG TERM RESISTANT AGAINST	SALTS WHICH MAY HARM BUILDING FABRIC, OILS, GREASES AND ACIDS

All technical data stated in this Technical Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control. The information, and, in particular, the recommendations relating to the application and end-use of CorrPRE's products, are given in good faith based on CorrPRE's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with CorrPRE's recommendations.

CorrPRE - Special Anodes Manufacturing, Zuidbaan 509, 2841MD, Moordrecht, Netherlands

Revision Nr.: 03

Revision date: 25-06-2025

Approved by: R. Giorgini